

Series 3170 Overlaminate

Intermediate Cast Overlaminate Pressure-Sensitive Film

Series 3170 overlaminate is a 1.3-mil (35 micron) gloss cast vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect printed graphics, the thinner facestock of Series 3170 provides a higher conformability for your vehicle wraps, intermediate signage, and graphics. Series 3170 is rated for outdoor durability up to 7 years. This product is not designed to be used as an optically clear window film, or to be used with cast digital films.

APPLICATIONS & FEATURES

- Protective overlaminate for Fusion Wrap, CalWrap, DPF 4600LX, DPF 4500GLX/MLX.
- Vehicle and fleet graphics, intermediate signage, kiosks and POP displays.
- Arlon overlaminate film is designed to be laminated cold without any heat.

PERFORMANCE & PHYSICAL DATA

/	/	
TEST METHODS	TYPICAL VALUE	
Gloss Meter 60° Reflection	80 to 90 Gloss Units	
Micrometer, Federal Bench Type	1.3 mil (35 micron)	
Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 6.5 lb/in	≥ 1.2 kg/cm
Instron Tensile Tester as above	≥ 200%	
Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
On clean, dry substrate		
Flat:	40°F to 100°F	4.4°C to 38°C
Corrugated with rivets & channels:	60°F to 100°F	15°C to 38°C
On clean, dry substrate	-40°F to 175°F	-40°C to 79°C
Shrinkage After 158°F (70°C), 48 hours	< 10-mil	0.25 mm
PSTC-1, 15 min, 70°F (21°C)	3.0 lbs/in	0.535 kg/cm
TLMI Release at 90°, 300 in/min (760 cm/min)	37 g/2in	7.28 g/cm
	Gloss Meter 60° Reflection Micrometer, Federal Bench Type Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction Instron Tensile Tester as above Ideal Storage Temperature 70°F (21°C) and 50% relative humidity On clean, dry substrate Flat: Corrugated with rivets & channels: On clean, dry substrate Shrinkage After 158°F (70°C), 48 hours PSTC-1, 15 min, 70°F (21°C)	Gloss Meter 60° Reflection Micrometer, Federal Bench Type 1.3 mil (35 micromoters) Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction Instron Tensile Tester as above ≥ 200% Ideal Storage Temperature 70°F (21°C) and 50% relative humidity 2 years from fact On clean, dry substrate Flat: 40°F to 100°F Corrugated with rivets & channels: 60°F to 100°F On clean, dry substrate Shrinkage After 158°F (70°C), 48 hours > 40°F (21°C) 3.0 lbs/in

Standard Terms & Conditions Apply

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.